



HYCHEM

Infrastructure

SPETEC® STOP H100

SEMI RIGID INJECTION RESIN FOR SEALING LEAKING CRACKS AND JOINTS



Product description

One component, closed cell, hydrophobic, water reactive, phthalate free, low viscosity polyurethane injection resin for stabilisation and water cut-off of large water leaks. In contact with water the SPETEC® STOP H100 will expand and set as a permanent water seal inside the crack or joint.

Field of application

- Water cut-off of large flow and high pressure water leaks.
- Water cut-off of water leaks in foundations such as diaphragm walls, piling sheets and secant piles.
- Stabilisation and water cut-off of large cracks, voids and gravel layers.
- Pre and post injections in mines, tunnels, pipe jacking, drill & blast and TBM applications.
- Injections in combination with cement-based grout, “combi-grouting”.
- Crack and gravel layer injections in concrete structures.
- Soil stabilisation and anchors in porous geology.
- Water cut-off of sewer water leaks and sewer stabilisation.
- Probe Grouting for below grade pipes.
- Manhole Injections.

Advantages

- Single component system.
- Different reaction times are possible by adjusting the percentage of SPETEC® Gen Ace (accelerator). To get an even faster reaction, there is also a SPETEC® Gen Ace Fast accelerator available.
- Cured polyurethane exhibits high strength and good chemical resistance. (contact our Technical Service for more information)
- Cured polyurethane is harmless for the environment and resistant to biological attack.

Application

Note: the following is a typical application description. In case of other jobsite parameters, please contact our technical department

Preliminary analyses

For leaking joints, check how the joint runs into the construction. Injection holes have to be drilled into the joint. For leaking cracks, drill the injection holes in a zigzag pattern around the crack to make sure that the injection hole intersects with the crack.



Required Tools

- Drill and drill bits of appropriate diameter and length.
- Packers of appropriate diameter and length.
- Manual, pneumatic or electric injection pump.



SPETEC® STOP H100

Preparation of the substrate

- Drill under an angle of 45° into the crack or joint. Ideally the injection hole should intersect the joint or crack about half way the thickness of the wall or slab.
- Blow the dust out of the injection hole.
- Fix a packer of the right diameter into the injection hole.

Preparation of the product

- Read the technical and safety data sheets prior to commencement of the injection works.
- Vigorously shake the SPETEC® Gen Ace or the SPETEC® Gen Ace Fast accelerator before use and add the required quantity (2-10%) into the SPETEC® STOP H100 resin.
- Mix the accelerator homogeneously into the resin and protect against moisture and rain to prevent premature reaction.
- Only prepare that amount of product that can be processed in one day.

Preparation of the equipment

- Depending on the application, injection can be carried out using a hand pump, pneumatic pump or electric pump. Preferably use a separate pump for injection of water and PU resin.
- Check that the pump is working properly.
- Prior to injection, the pump must be flushed with SPETEC® PUMP CLEANER and be completely free of water to prevent pump blockage.

Injection

- Start the injection at the first packer; for vertical joints or cracks this is usually the lowest packer.
- Do not over pressurise while injecting; the correct injection pressure is the pressure that allows the resin to flow into the crack or joint. Avoid injecting at pressures of more than 100 bars.
- If unreacted resin comes out of the joint or crack, stop the injection and move on to the next packer.
- After the last injection of resin into the packer, shoot a little bit of water into the packer in order to make sure that the last injected resin will react as well.

Finishing

After injection, remove the packers from the concrete and fill the holes with a fast setting cement or any other appropriate filler material.

Application conditions

Avoid injecting by temperatures below -20°C. In extreme cold conditions it is recommended to warm the resin and catalyst.

Cleaning and maintenance

After the injection, clean the pump with SPETEC® PUMP CLEANER. If the pump will not be used for several days, put oil into the pump and leave it there until the next usage. Never rinse the pump with water.

Complimentary products

SPETEC® PUMP CLEANER
SPETEC® PACKERS & ACCESSORIES
CERMIPLUG

Advice/Focal points

Water must always be present during the injection of SPETEC® STOP H100 as it is a water-reactive resin.



SPETEC® STOP H100

Technical Data

APPEARANCE

SPETEC STOP H100, uncured (appearance: brown liquid)		
Viscosity at 25°C	Brookfield SP3 – 200rpm	±180 mPa.s
Density	EN ISO 2811-1	±1,05 kg/dm ³

SPETEC Gen Ace, Accelerator for SPETEC STOP H100 (appearance: yellow – orange liquid)		
Viscosity at 25°C	Brookfield SP3 – 200rpm	±75 mPa.s
Flash point		157°C
Density	EN ISO 2811-1	±1,05 kg/dm ³

SPETEC Gen Ace Fast, Accelerator for SPETEC STOP H100 (appearance: yellow – orange liquid)		
Viscosity at 25°C	Brookfield SP3 – 200rpm	±70 mPa.s
Flash point		157°C
Density	EN ISO 2811-1	±1,05 kg/dm ³

Technical Data

REACTION TIMES

SPETEC Gen Acc	5°C			15°C			25°C		
	Start	End		Start	End		Start	End	
2	100"	440"	16V	86"	450"	15V	33"	200"	17V
6	32"	120"	16V	20"	105"	17V	14"	79"	20V
10	26"	26"	17V	18"	64"	18V	10"	45"	21V

SPETEC Gen Ace Fast	5°C			15°C			25°C		
	Start	End		Start	End		Start	End	
2	50"	240"	17V	35"	175"	17V	28"	155"	18V
6	30"	95"	17V	15"	57"	18V	12"	45"	20V
10	15"	40"	17V	12"	33"	18V	8"	28"	21V

Consumption

Consumption has to be assessed on site and is influenced by the amount of water leaking, thickness of the concrete slab or wall, presence of voids in and around the concrete etc.

Chemical resistances

Cured polyurethane exhibits good chemical resistance, is harmless for the environment and resistant to biological attack. Contact our Technical Service for more information.



SPETEC® STOP H100

Reference documents



Packaging

SPETEC® STOP H100	5 kg	Metal cans	92 pails/pallet
	20 kg	Pails	24 pails/pallet
	200 kg	Steel drums	4 drums/pallet
SPETEC® Gen Acc	0,5 kg	Plastic Bottles	12 bottles/box 40 boxes/pallet
	2 kg	Plastic Bottles	4 bottles/box 44 boxes/pallet
	20 kg	Metal Cans	24 pails/pallet
SPETEC® Gen Acc Fast	2 kg	Plastic Bottles	4 bottles/box 44 boxes/pallet

Storage and shelf life

SPETEC® STOP H100 is moisture sensitive and should be stored in a dry area between 5°C and 30°C.

Shelf life of the resin: 24 months in original packaging.

Shelf life of the accelerator: 24 months in original packaging.

Once opened, containers should be used as soon as possible.

Safety precautions

Avoid contact with eyes and skin, always use personal protective equipment in compliance with local regulations.

Read the relevant Material Safety Data Sheet before use.

Warranties and Disclaimers

Hychem warrants that this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product is dependent upon the proper use and application of the product by the applicator. Hychem has no role in the application of the finished polymer other than to manufacture and supply its components. It is vital that the person applying this product understands the product and is fully trained and certified in the use of spray equipment and application of sol-gel materials. There are no warranties that extend beyond the description on the face of this instrument, except when provided in writing, directly by Hychem and executed under seal by a company officer.

Field Support

Field support where provided, does not constitute supervisory responsibility. Suggestions made by HYCHEM either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they and not HYCHEM are responsible for carrying out procedures appropriate to a specific application.

Customer Responsibility

The technical information and application advice given in this publication is based on the best information available at the time of print.

As the information herein is of a general nature, no assumption can be made as to the product suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use.