



QuakeWrap® B2408G

Product Description

QuakeWrap® B2408G is a high-strength, high-modulus, non-corrosive biaxial glass fabric. The 0°/90° E-glass fabric has slightly different strengths in the longitudinal (0°) and transverse (90°) directions. A glass mat is stitched to the back of the original QuakeWrap B2408G fabric to provide water-proofing. QuakeWrap® B2408G is impregnated in the field using QuakeBond™ 300SR saturating resin to form glass fiber reinforced polymer (GFRP) for use in the strengthening, repair, and water-proofing of structural elements and infrastructure.

Uses

- Strengthening of structural elements in buildings, bridges, and other structures due to increased loads
- Seismic retrofit of structural elements such as columns, unreinforced masonry walls, shear walls, and diaphragms
- Repair of large diameter pipes and culverts to achieve strengthening and water-proofing
- Repair of damaged structural components caused by aggressive environments, fire, vehicle impact, aging, etc.
- Changes in structural system: new openings in floors, removal of existing walls, etc.
- Correction of design or construction errors

Advantages

- Glass mat layer provides water-proofing when saturated with QuakeBond™ 300SR
- Strong and lightweight fabric ideal for confined spaces
- Single layer provides strength in two orthogonal directions
- Provides flexure and shear strengthening in single layer application
- Fully compatible and excellent adhesion to QuakeBond™ resins
- Non-corrosive; provides directional barrier
- Can be formed to strengthen and repair complex shapes
- Light weight; does not alter dead load of structure
- Special manufacturing of the fabric reduces potential of fraying

Coverage

40 ft² per 1-gallon QuakeBond™ 300SR

Surface Preparation

Surface must be clean and sound; it may be dry or damp but must be free of standing water and frost. Remove dust, laitance, grease, curing compounds, disintegrated materials and other bond inhibiting materials from the surface. Existing uneven surfaces must be filled with an appropriate repair mortar.

Minimum tensile strength of 200 psi (1.4 MPa) with substrate failure is required. Any sharp edges (i.e. fins, form-marks, etc.) must be ground smooth and flush. Sharp edges must be rounded to a minimum diameter of 3/4 in. (19mm). Contact a QuakeWrap representative for variances in surface preparation.



QuakeWrap® B2408G

Properties of Fabric Laminated with 300SR

	US UNITS	SI UNITS
Aerial Weight Fabric Only	20 oz/yd ²	678 g/m ²
Ply Thickness	0.056 in.	2.03 mm
Longitudinal (0°) Direction:*		
Tensile Strength	25.7 ksi	177.2 MPa
Tensile Modulus	1,744 ksi	12,024 MPa
Ultimate Elongation	<2%	<2%
Breaking Force	1,430 lb/in	328 N/mm
Transverse (90°) Direction:*		
Tensile Strength	24.3 ksi	167.5 MPa
Tensile Modulus	1,702 ksi	11,735 MPa
Ultimate Elongation	<2%	<2%
Breaking Force	1,360 lb/in.	243 N/mm

* Results based information by fabric manufacturers historical data and testing. Values provided are ultimate capacity and shall be reduced per design engineers' judgment of application.

Application

- Saturate QuakeWrap® B2408G fabric thoroughly with QuakeBond™ saturating resins; for more details refer to the Product Data Sheet for the saturants.
- Before the resin hardens, apply saturated fabric to the substrate surface that has been coated with QuakeBond™ 220UR or other QuakeWrap approved adhesive.
- Using gloved hands, carefully remove any entrapped air bubbles under the fabric; a plastic laminating roller can be used for this purpose. If required, additional layers of saturated fabric can be directly applied on top of previous layers.
- Feather the edges of the fabric with QuakeBond™ 220UR.

Installation of QuakeWrap® fabrics must be performed only by specially trained and approved contractors.

Fabric can be cut to appropriate length using commercial quality heavy-duty scissors. Since dull or worn cutting tools can damage, weaken or fray the fiber, their use should be avoided.

Cleanup

Dispose of waste in accordance with local disposal regulation. Cured materials can only be removed mechanically. See QuakeBond™ 300SR and 220UR SDSs for more information on resin cleanup.

Packaging

- Rolls: 50 in. X 70 yards (1.27 m X 75 m).
- The fabric can be easily cut in the field to various lengths.



QuakeWrap® B2408G

Shelf life and Storage

Shelf life is unlimited in proper storage conditions. Store in a dry environment at 45°-95°F (7°-35°C).

Limitations

Design calculations must be made and certified by an independent licensed professional engineer. System is a vapor barrier. Concrete should not be encapsulated in areas of freeze/thaw.

Caution

QuakeWrap® B2408G is non-reactive. However, caution must be used when handling since a fine glass dust may be present on the surface. Gloves must be worn to protect against skin irritation. Caution must also be used when cutting the fabric to protect against airborne glass dust generated by the cutting procedure. Use of an appropriate, properly fitted NIOSH approved respirator is recommended.

First Aid

Appropriate Personal Protective Equipment (PPE) should be worn at all times when handling product.

Warranties and Disclaimers

Hychem warrants that this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product is dependent upon the proper use and application of the product by the applicator. Hychem has no role in the application of the finished polymer other than to manufacture and supply its components. It is vital that the person applying this product understands the product and is fully trained and certified in the use of spray equipment and application of sol-gel materials. There are no warranties that extend beyond the description on the face of this instrument, except when provided in writing, directly by Hychem and executed under seal by a company officer.

Field Support

Field support where provided, does not constitute supervisory responsibility. Suggestions made by HYCHEM either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they and not HYCHEM are responsible for carrying out procedures appropriate to a specific application.

Customer Responsibility

The technical information and application advice given in this publication is based on the best information available at the time of print. As the information herein is of a general nature, no assumption can be made as to the product suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use.