



VELOSIT® NG512

NON-SHRINK GROUT WITH HIGH PERFORMANCE FOR 12 - 120 MM

Product Description

VELOSIT NG 512 is a cementitious non-shrink grout for concrete substrates. It is used to fill large voids or underneath base plates of machinery or building columns up to 120 mm clearance. VELOSIT NG 512 is a double shrinkage compensated cementitious grout with quick strength development. VELOSIT NG 512 creates an extremely well bonded, high strength connection between concrete and concrete or concrete and steel. VELOSIT NG 512 is the result of many years in the field testing and research. VELOSIT NG 512 binds the mixing water quickly reducing or completely eliminating the need for water curing and protection.

Typical Applications

- Interior and exterior use
- Repair of large surface defects on concrete
- Filling of gaps between two concrete bodies
- Grouting of machinery and construction columns
- Application thickness from 12 mm to 120 mm
- Anchoring of starter bars and dowels
- Use as microconcrete

Features

- Product approved by TMR-QLD- MRTS72 + MRTS73
- Minimal shrinkage
- Slight volume increase in the plastic stage to ensure good bond to base plates
- Excellent workability
- Wide range of water addition allowing consistencies from plastic to fluid
- Fiber reinforced
- Advanced corrosion inhibitor technology
- 60 min. working time and 15 MPa compressive strength after 6 hours
- Open to foot traffic after 6 hours
- Water curing only under hot and dry conditions required for max. 4 hours

Technical Data

Colour	Gray	Compressive / flexural strength in fluid consistency (16% water per bag)	6 hours: 15 / 3 MPa 24 hours: 44 / 6 MPa 7 days: 78 / 9 MPa 28 days: 90 / 10 MPa
Mixing ratio by weight	100 : 15	Compressive Strength (12% water per bag)	28 Days: 100 MPa
Mixing ratio by volume	100 : 26	Chloride ions	< 0.05%
Density	1.7kg/L	Carbonation resistance	passed
Substrate temperature	5 - 35°C	Capillary water absorption	0.1kg/m ² x h0.5
Initial set	120 minutes	Adhesive strength*, concr.	2.5 Mpa
Final set	200 minutes	Restrained shrinkage*	2.2 Mpa
Fire rating EN13501-1	Class A1		

*acc. EN 1542. Adhesion depends very much on proper surface preparation!



VELOSIT® NG512

NON-SHRINK GROUT WITH HIGH PERFORMANCE FOR 12 - 120 MM

APPLICATION GUIDELINES

Surface Preparation

VELOSIT NG 512 is designed for concrete and steel substrates.

Steel must be prepared to a purity of SA 2.5 acc. SIS 05 5900.

Concrete substrates must be prepared with sand blasting, shot blasting or ideally high pressure water blasting (> 100 bar/1450 psi) to remove all bond breaking substances. Remove all carbonated concrete. Test with Phenolphthalein or other suitable indicator until concrete with sufficient alkalinity for rebar protection is reached. If rebar is exposed remove concrete at least 12 mm behind rebar to fully embed the steel into VELOSIT NG 512. Substrate must be rough, open porous and load bearing. The minimum requirement for adhesive strength is 2.0 MPa and for the compressive strength 30 MPa. Before the application of VELOSIT NG 512, dampen the substrate with clean water to a saturated surface dry (SSD) condition. Remove standing water puddles.

Mixing

Mix VELOSIT NG 512 with 12.5 – 15 % potable water, i.e. 2.5 – 3.0 l water per 20 kg bag. Fill the 12.5 % mixing water (2.5 l per bag) into a suitable bucket and mix the powder with a slow speed drill (300 – 600 rpm) into the water until a lump-free mix is achieved. Add up to 2.5 % water under stirring until the desired consistency is achieved. The product is workable for 60 min. at 23 °C.

Manual application

Pour VELOSIT NG 512 can be applied fresh in fresh into the prime coat. The product can be applied into voids of minimum 12 mm and up to 120 mm width. For smaller gaps use VELOSIT NG 511. Make sure to work in sections that can be finished within 15 min. Cooler temperatures extend, warmer temperatures reduce the working time. Rebars and other penetrations must be fully embedded into the mortar. If grouting underneath large base plates use a fluid consistency. The max. travel distance of the grout depends on the min. clearance of the gap. Without forcing the material the travel distance is approx. the gap width multiplied by 50. For example a 50 mm gap allows 2.5 m travel distance just by gravity.

Pump application

Suitable grouting pumps are for example:

- PFT GmbH: PFT G4
- HighTech GmbH: HighComb Big
- Wagner GmbH: PC 25
- Putzmeister GmbH: SP12 or MP 25

In mixing pumps feed the powder into the product hopper and adjust the water to the desired consistency. With grout pumps add the mixed product as described under „Mixing“ into the feed hopper of the pump and pump continuously. Long spray interruptions may result in clogging of the spray hose. The product may cure a lot faster if the hose is exposed to direct sunlight. Always empty and flush the machine after pumping or before long work interruptions. VELOSIT NG 512 is a fast curing material and may be hard to remove if left in the machine. Never vibrate VELOSIT NG 512 to increase flow. Use wood or a steel rod to move the material in place.

Curing

VELOSIT NG 512 does not require long term curing as it reacts relatively fast with water. Only under hot weather or very dry conditions water curing for max. 4 hours is required.



VELOSIT® NG512

NON-SHRINK GROUT WITH HIGH PERFORMANCE FOR 12 - 120 MM

Coverage

Volume per bag:

20 kg* VELOSIT NG 512 result in approx. 10.4 litre cured mortar.

* 20 kg VELOSIT NG 512 powder + 2.8 kg water, i.e. 22.8 kg mixed material per bag

Packaging

20kg watertight plastic bags

Warning

Wear appropriate personal protection equipment. Gloves, eye protection, mask and overalls should be used during mixing and application.

Clean up

VELOSIT NG 512 can be removed in the fresh state with water. Once it has cured acidic cleaners like muriatic acid and mechanical cleaning are required.

Storage

In unopened original packs for 12 months at 5 – 35 °C in a dry storage place protected against sunlight.

Safety

Please observe the actual valid material safety data sheet and follow the described safety measures for handling of the product.

Warranties and Disclaimers

Hychem warrants that this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product is dependent upon the proper use and application of the product by the applicator. Hychem has no role in the application of the finished polymer other than to manufacture and supply its components. It is vital that the person applying this product understands the product and is fully trained and certified in the use of spray equipment and application of sol-gel materials. There are no warranties that extend beyond the description on the face of this instrument, except when provided in writing, directly by Hychem and executed under seal by a company officer.

Field Support

Field support where provided, does not constitute supervisory responsibility. Suggestions made by HYCHEM either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they and not HYCHEM are responsible for carrying out procedures appropriate to a specific application.

Customer Responsibility

The technical information and application advice given in this publication is based on the best information available at the time of print. As the information herein is of a general nature, no assumption can be made as to the product suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use.