



VELOSIT® RM202

UNIVERSAL VERTICAL & OVERHEAD REPAIR MORTAR

Product Description

VELOSIT RM 202 is a cementitious repair mortar for all types of construction substrates. It creates a good surface for coatings and overlays. VELOSIT RM 202 is a shrinkage compensated cementitious repair mortar with very quick strength development. VELOSIT RM 202 is the result of many years in the field testing and research. VELOSIT RM 202 creates an extremely well bonded, rigid abrasion resistant layer on the substrate.

Typical Applications

- Repair of large surface defects on concrete
- Overlays and repairs on concrete structures like dams, bridges, beams, balconies, facades
- Application on horizontal and vertical incl. overhead areas
- Filling of blow holes, honeycombs and surface roughness
- Application thickness from feather-edge to 100 mm
- Re-modeling of architectural features requiring a moldable mortar that can be shaved into shape

Features

- Approved by AWQC - AS/NZS 4020:2018
- Minimal shrinkage/expansion under dry resp. wet curing conditions minimizing the risk of micro-cracking
- Excellent workability especially overhead
- Fiber reinforced
- 40 min. working time and 15 MPa compressive strength after 4 hours
- Final strength of more than 50 MPa after 28 days
- Open to foot traffic after 3 – 4 hours
- Good resistance against CO₂ and Chloride penetration due to a very tight pore structure
- Good resistance against aggressive media with a pH range of 3-12 and against soft water with low ion content
- Good weathering resistance
- Good sulfate resistance

Technical data

Colour	Gray	Initial set	55 minutes
Mixing ratio by weight	100 : 17	Final set	120 minutes
Mix ratio by volume	100 : 27	Compressive / flexural strength	4 hours: 15 / 2 MPa 24 hours: 31 / 5 MPa 7 days: 45 / 8 MPa 28 days: 56 / 9 MPa
Density	1.6 kg/L	Adhesive strength *	primed with RM 202: 1.8 MPa primed with CP 201: 2.2 MPa
Substrate temperature	5 - 35°C	Restrained shrinkage*	1.5 MPa

*acc. EN 1542. Adhesion depends very much on proper surface preparation!



VELOSIT® RM202

UNIVERSAL VERTICAL & OVERHEAD REPAIR MORTAR

APPLICATION GUIDELINES

Surface Preparation

VELOSIT RM 202 is designed for mineralic substrates like concrete, masonry or absorptive natural stones. Steel may be coated with a suitable bonding bridge.

Steel must be prepared to a purity of SA 2.5 acc. SIS 05 5900. Apply a corrosion protection coat on rebar with VELOSIT CP 201. Other steel areas can be primed with Hychem E100SS or E500P with a full broadcast. Steel may expand and contract differently under temperature changes than a cementitious mortar. Thus steel application is only recommended if steel is embedded in larger concrete bodies or the temperature is not subject to major changes.

Mineralic substrates (concrete, masonry, cement compatible natural stones) must be prepared with sand blasting, shot blasting or ideally high pressure water blasting (> 100 bar) to remove all bond breaking substances. On reinforced concrete remove all carbonated concrete. Test with Phenolphthalein or other suitable indicator until concrete with sufficient alkalinity for rebar protection is reached. If rebar is exposed remove concrete at least 6 mm behind rebar to fully embed the steel into VELOSIT RM 202. Substrate must be rough, open porous and load bearing. The minimum requirement for adhesive strength is 1.5 MPa and for the compressive strength 25 MPa. Lower strength values can be accepted if lower adhesive strength is acceptable. Active water leaks must be treated and fully stopped with VELOSIT PC 222. Leaking cracks need to be sealed with Hychem Spetec PU. Before the application of VELOSIT RM 202, dampen the substrate with clean water to a saturated surface dry (SSD) condition.

Concrete repair acc. EN 1504-9 principle 3, 4 or 7 requires a prime coat with VELOSIT CP 201 on concrete and rebar surface to ensure best adhesion strength results.

Mixing

Mix VELOSIT PRM 202 with 15 – 18 % potable water, i.e. 3.0 – 3.6 l water per 20 kg bag. Fill the 15 % mixing water (3.0 l per bag) into a suitable bucket and mix the powder with a slow speed drill (300-600 rpm) into the water until a lump-free mix is achieved. Add more water (max. 3 %) under stirring until the desired consistency is achieved. The product is workable for 40 min. at 23 °C.

Priming

Apply a prime coat of VELOSIT RM 202 with a wet sponge to the pre-dampened substrate. Work approximately 0.5 – 1 kg per m² into the surface pores. If working acc. to EN 1504-9 the prime coat must be applied with VELOSIT CP 201! Trowel application Trowel VELOSIT RM 202 fresh in fresh into the prime coat. The product can be applied up to 100 mm on vertical areas. Larger overhead areas may limit the thickness to max. 50 mm. Make sure to work in sections that can be finished within 40 min. Rebars and other penetrations must be fully embedded into the mortar.

Spray application

Use suitable spray machines such as:

- PFT GmbH: PFT G4
- HighTech GmbH: HighComb Big
- Wagner GmbH: PC 25
- Putzmeister GmbH: SP12 or MP 25
- Inotec GmbH: INOMAT-M8

In mixing pumps feed the powder into the product hopper and adjust the water to the desired consistency. With mortar pumps add the mixed product as described under "Mixing" into the feed hopper of the spray machine and spray continuously. If a smooth surface is required, follow with a trowel shortly after material is sprayed. Work in sections. Long spray interruptions may result in clogging of the spray hose. The product may cure a lot faster if the hose is exposed to direct sunlight. Always empty and flush the machine after spraying or before long spray interruptions. VELOSIT RM 202 is a fast curing material and may be hard to remove if left in the machine.



VELOSIT® RM202

UNIVERSAL VERTICAL & OVERHEAD REPAIR MORTAR

Re-modeling of architectural features

Once VELOSIT RM 202 applied by trowel or spray machine has started to set it can be sculpted as needed. Shave off material in thin layers to achieve desired form. If needed finish surface with a slightly wet sponge to remove surface imperfections and air voids.

Curing

VELOSIT RM 202 does not require long term curing as it reacts relatively fast with water. Only under hot weather or very dry conditions water curing for 3 – 4 hours is required.

ESTIMATING

Repair of surface defects

20 kg VELOSIT RM 202 result in approx. 12,5 litre cured mortar.

Surface Coating:

10 kg* VELOSIT RM 202 per m2 for 6 mm dry mortar thickness on smooth substrates. Depending on surface roughness application rates can be significantly higher.* 10 kg VELOSIT RM 202 powder + 1.7 kg water, i.e. 11.7 kg mixed material per 6 mm and m2.

CLEAN UP

VELOSIT RM 202 can be removed in the fresh state with water. Once it has cured acidic cleaners like muriatic acid and mechanical cleaning are required.

PACKAGING

20 kg watertight plastic bags.

STORAGE

In unopened original packs for 12 months at 5 – 35 °C in a dry storage place protected against sunlight.

SAFETY

Please observe the actual valid material safety data sheet and follow the described safety measures for handling of the product.

Warranties and Disclaimers

Hychem warrants that this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product is dependent upon the proper use and application of the product by the applicator. Hychem has no role in the application of the finished polymer other than to manufacture and supply its components. It is vital that the person applying this product understands the product and is fully trained and certified in the use of spray equipment and application of sol-gel materials. There are no warranties that extend beyond the description on the face of this instrument, except when provided in writing, directly by Hychem and executed under seal by a company officer.

Field Support

Field support where provided, does not constitute supervisory responsibility. Suggestions made by HYCHEM either verbally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they and not HYCHEM are responsible for carrying out procedures appropriate to a specific application.

Customer Responsibility

The technical information and application advice given in this publication is based on the best information available at the time of print. As the information herein is of a general nature, no assumption can be made as to the product suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by Commonwealth or State Legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use.